



APPLICATION

SYNTHETIC RESINS - PAINT AND VARNISH /Solvent Based

2 K ACRYLIC RESIN

IZELCRYL 18X60 LV 1.8 %OH

STARTING PAINT FORMULATION

| COMPONENT | AMOUNT % |
|-------------------|----------|
| IZELCRYL 18X60 LV | 50 |
| DISPERSION AGENT | 0,5 |
| ANTI COLLAPSE | 0,3 |
| CALCITE | 35 |
| CARBON BLACK | 1,5 |
| SOLVENT | 12,7 |

* In paint formulation, resin solid rate is between 30-35% and paint solid ratio is between 65-70%.

PAINT AND VARNISH PROPERTIES

| TEST | VARNISH | PAINT |
|--|----------|----------|
| Drying(minute, 20-23°C) | 15 | 20 |
| Hard Drying(hour, 20-23°C) | >24 | >24 |
| Pot life(hour, 20-23°C) | >24 | >24 |
| Gloss(60°, 20-23°C) | 89 | 80 |
| Pendulum Hardness(1-5 day/counts ,20-23°C) | 70p-182p | 85p-195p |
| *Yellowing Resistance(20-23°C) | 3 | - |
| *Cross Cut(GAL/AL/SHT) | 2\3\1 | 2\3\1 |
| *Impact Strength(5N/1000g)(GAL/AL/SH) | 2\3\2 | 2\3\2 |
| *Conical Bend Test(20-23°C)(GAL/AL/SHT) | 2\2\2 | 2\2\2 |
| **Abrasion Test(1000 cycle/500 gr) | 0,385 | 0,464 |

(*)Marked areas are rated as 0 best and 5 worst.

Galvanized(Gal),Sheet(SHT),Aluminum(AL)

(**) Taber Abrasion Test performed according to the mass method

TaberWear Index = $(F_{\text{total}} \times T) / n$ $F_{\text{total}} = A_{\text{first}} - B_{\text{End}}$ n= cycle T = mass loss at an average of 1000 cycle



Figure1. Aluminum surface impact test



Figure 2. Galvanized surface impact test




Figure 3. Sheet metal impact test



Figure 4. Aluminum surface adhesion test



Figure 5. Galvanized surface adhesion test



Figure 6. Sheet metal surface adhesion test



Figure 7. Yellowing resistance

Note: Experiments were carried out under Izel Kimya laboratory conditions aimed to give information about the product features. Results may vary according to the user and application condition